



QUIK-SHIELD 2910

Stitchbonded Roofing Fabric - Soft 3 oz.

QUIK-SHIELD® 2910 is a 3 oz. stitchbonded-style polyester fabric used in the reinforcement of cold process roofing systems. It is also used as a flashing reinforcement with mastics and elastomerics. QUIK-SHIELD® 2910 has superior strength and elongation making it an excellent reinforcement for water base cold process and maintenance roof systems. In narrow widths, it is used as a reinforcement in elastomeric metal roof systems.

TYPICAL PHYSICAL PROPERTIES

Properties achieved in a lab environment at 77°F. Field conditions may cause variation in properties.

	PROCEDURE	VALUES
Burst Strength (lbs.)	D-3786	127
Elongation (%)	D-1682	25
Tensile Average (lbs.)	D-1682	41
Thickness (in.)		0.25
Trapezoid Tear Strength (lbs.)	D-1117	14
Weight (oz. per sq. yd.)		3

PRODUCT INFORMATION

Product Packaging 4 inch rolls (4" x 300"), 6 inch rolls (6" x 300"), 12 inch rolls (12" x 300"), 18 inch rolls (18" x 300").

APPLICATION

QUIK-SHIELD® 2910 will provide good conformability on smooth or semi-smooth surfaces, such as cap sheet and filled or spudded gravel. QUIK-SHIELD® 2910 has a close knit that may require light brooming to ensure good embedment and removal of any air pockets.



The information herein is believed to be reliable; however, unknown risks may be present. SWD Urethane makes no warranty, expressed or implied, concerning this product's merchantability or fitness for any particular use. The product will meet the written liquid component specifications as indicated on the technical data sheet published at the time of the purchase. The entirety of SWD Urethane's responsibility is limited only to the cost of the SWD material. The foregoing constitutes SWD Urethane's sole obligation with respect to damages, whether direct, incidental or consequential, resulting from the use or performance of the product.

Safety is the responsibility of the owner, the owner's appointed representative, the contractor, and/or inspector. Become familiar with local, state, and federal regulations regarding chemical health, safety, and handling. For more information consult the product SDS, contact the SPFA (www.sprayfoam.org) or the ACC (www.spraypolyurethane.org).

SWD Urethane | 800-828-1394 | 540 South Drew St. | Mesa, AZ 85210 | swdurethane.com

DOC ID: SWD-TDS-PMG-369 REV. 00 EFF. DATE 06/15/20 APPROVAL: MGMT. REP. **ON FILE**